

AMENDMENTS TO THE SPECIFICATION

At page 28 of the Specification, please replace Table 2 with the following replacement

Table 2:

Table 2

	Inorganic Particles			Polymer Particles			Di + 50 nm	Ratio of Contents (Cp/Ci)	Polishing Rate (nm/min)
	Kind	Average Particle Size Di (nm)	Content (Effective Ingredient)	Kind	Average Particle Size Dp (nm)	Content (Effective Ingredient)			
Ex. 1	(1)	11	20	a	40	3	61	0.15	130
Comp. Ex. 1	(1)	11	20	—	—	—	—	—	30
Ex. 2	(2)	26	13	a	40	3	76	0.23	350
Comp. Ex. 2	(2)	26	13	—	—	—	—	—	110
Ex. 3	(3)	45	13	b	54	3	95	0.23	390
Ex. 4	(3)	45	13	f	71	3	95	0.23	430
Comp. Ex. 3	(3)	45	13	—	—	—	—	—	180
Ex. 5	(4)	85	13	c	80	3	135	0.23	650
Comp. Ex. 4	(4)	85	13	—	—	—	—	—	210
Ex. 6	(5)	120	13	e	138	3	170	0.23	560
Comp. Ex. 5	(5)	120	13	—	—	—	—	—	90
Ex. 7	(5)	160	13	e	138	3	210	0.23	140
Comp. Ex. 6	(5)	160	13	—	—	—	—	—	70